



Two-component Scraping Type Marking Paint

TECHNICAL DATA SHEET (TDS)

Standard	EN1436:2007
Binder	Active Acrylic Resin
Specific gravity	1.99kg/L
Volume Solid	98%
Weight Solid	98%
Volatile Organic Compound	Non
Theoretical Spreading Rate	3-3.5 kg/m ² (dot area accounted for 60%, wet film thickness 1mm)
Dry speed	< 20 minutes (25°C)
Hardener	powder / liquid
Color	white, yellow
Storage	Dry, cool, binder and hardener should be stored separately.
Expiration	One year