

Product Name: Bituminous Road Markers Adhesive

Standard Name: ASTM test Method

Product Code:RMA088

PROPERTIES:

Specification	Test Method	Requirements	Test Value
Softening Point, °C	ASTM D 36	93 - 129	113
Penetration, 25°C , mm x 10-1	ASTM D 5	10 - 18	11
Penetration, 60°C, mm x 10-1	ASTM D 5	45 - 65	51
Rotational Viscosity @ 204°C , Pa.s	ASTM D 4402	3.0 – 7.5	3.6
Flow @ 70°C, mm	ASTM D 5329	5 max	2
Specific Gravity, 25°C	ASTM D 71	1.6 – 1.85	1.78
Flash Point, °C	ASTM D-92	288 min	295
Filler By Weight		65-72%	70.9%
Recommend Pour Temperature		191-218°C	191-218°C

Function:

Heated Bituminous Road Markers Adhesives

Grades:

- 0 centigrade
- 10 centigrade
- 20 centigrade
- 30 centigrade
- 40 centigrade

Temperature:

Using Temperature suitable From -90centigrade to 90 centigrade

Labelling:

Landscapus Inc

Packaging:

2.75Kgs/BLOCK with Plastic Bags, 4 blocks @11Kgs in one 32cm*24cm*20cm Box

Shelf Life:

12 months from manufacturing date

User advice:

Contact us for any other questions