

Product Name: Crack Sealing Tape

Standard Name: ASTM test Method

Product Code:RMA090

PROPERTIES:

Specification	Test Method	Requirements	Test Value
Softening Point	ASTM D 36	170°F (77°C) minimum	99
Brookfield Viscosity, 400°F (204°C)	ASTM D2669	4,000 - 10,000 cP	6200
Cone Penetration, 77°F (25°C)	ASTM D5329	60-100	71
Flow, 140°F (60°C)	ASTM D 5329	5 mm maximum	3
Resilience 77° F (25° C) :	ASTM D5329	30% min	59.5
Ductility: 77° F (25° C) :	ASTM D113	30 cm min	50
Ductility: 39.2° F (4° C) :	ASTM D113	30 cm min	50
Tensile Adhesion,1" Specimen, 24 hour dry blocks	ASTM D5329	500% minimum	720
Flexibility, 1/8" (3.2 mm) specimen, 90° bend, 10 sec, 1" (25 mm) mandrel	ASTM D3111	Pass at 0° F (-18°C)	Pass
Asphalt Compatibility	ASTM D 5329	Pass	Pass
Recommend Pour Temperature		193-204°C	Pass

Function:

1. Heated Bitumious Adhesive, Bonds raised road markers, delineator posts, curbstones, turtle markers, Speed Humps and other objects which can be bonded to the road surface.
2. Road cracking sealing.

Sizes:

3CM*2.5MM	3CM*3MM	4CM*2.5MM	4CM*3MM	6CM*2.5MM
-----------	---------	-----------	---------	-----------

Packaging:

Each 10rolls With Plastic Bags in carton Box

Shelf Life:

12 months from manufacturing date

User advice:

Contact us for any other questions



Before Sealing



After Sealing With Tapes

